



TECHNICAL DATA SHEET

Date of issue: 2020

TETRACRYL

DESCRIPTION

Acrylic, elastomeric, water repellent wall plaster ready to use. It has excellent adhesion to all masonry types like concrete, plaster, cement, etc. Does not need to be over-coated by paint. Due to its elasticity is ideal as topcoat to the constructions for subsequent insulation of buildings.



TECHNICAL CHARACTERISTICS

Density	:	1,75 - 1,85 (ΕΛΟΤ EN ISO 2811 20°C)																
Viscosity	:	45.000 - 55.000 mPas (ASTM D2196-86 25°C)																
pH	:	8.6 - 8.9 (ASTM E70)																
Thinning	:	Without dilution																
Coverage	:	1,5-3,1 kg/m ² depend on the granule size ,the desired decorative finish and the use																
		<table border="1"><thead><tr><th>Product</th><th>Granule size</th><th>Thickness of layer</th><th>Consumption</th></tr></thead><tbody><tr><td>TETRACRYL</td><td>1mm</td><td>1mm</td><td>1.5-1.8kg/m²</td></tr><tr><td>TETRACRYL</td><td>1.5mm</td><td>1.5mm</td><td>2.0-2.5kg/m²</td></tr><tr><td>TETRACRYL</td><td>2mm</td><td>2mm</td><td>2.8-3.1kg/m²</td></tr></tbody></table>	Product	Granule size	Thickness of layer	Consumption	TETRACRYL	1mm	1mm	1.5-1.8kg/m ²	TETRACRYL	1.5mm	1.5mm	2.0-2.5kg/m ²	TETRACRYL	2mm	2mm	2.8-3.1kg/m ²
Product	Granule size	Thickness of layer	Consumption															
TETRACRYL	1mm	1mm	1.5-1.8kg/m ²															
TETRACRYL	1.5mm	1.5mm	2.0-2.5kg/m ²															
TETRACRYL	2mm	2mm	2.8-3.1kg/m ²															
Drying time	:	Touch dry after 1 hour and recoat able after 2-3hours																
Colors	:	Unlimited number of shades through tinting system of TETRALUX.																
Packaging	:	18kg, 25kg																
VOC (Volatile Organic Compounds)	:	EU limit value for this product Category A: "i", Type:WB, One pack performance coatings: 140g/l (2010). This product contains <140g/l VOC.																
Painting tools	:	Spatula or appropriate machine Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.																

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS & Co E.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, www.tetralux.gr, e-mail: contact@tetralux.gr



TECHNICAL DATA SHEET

Date of issue: 2020

Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.

APPLICATION

Stir well before use

The substrate must be clean, dry and free of foreign matter and substances. First apply a layer with the special primer SOVADUR or TETRADUR primer (waterproof substrates with high penetration and strong adhesion). After the primer dries we stir the material well and apply it using a stainless polished spatula or an appropriate plaster sprayer gun. While the Tetracryl layer is fresh (about 15-20 minutes later), the surface finish is "pressed" or "scrubbed" using a plastic spatula. Do not apply at temperatures below 10°C and above 35°C and relative humidity above 80%.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Keep out of reach of children • If medical advice is needed, have product container or label at hand • Do not get in eyes, on skin, or on clothing. • Call a POISON CENTER or doctor/physician if you feel unwell • Dispose of contents/container in accordance with applicable regional, national and local laws and regulations

Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist

Contains: 2-methylisothiazol-3(2H)-one, reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1). May produce an allergic reaction.

Tel. POISON CENTER: 210 7793777