



## TECHNICAL DATA SHEET

Date of issue: 2021

### 262 CONCRETE FLOORS ACRYLIC VARNISH

#### DESCRIPTION

Quick drying acrylic solvent based acrylic varnish. Specially designed to protect floors with stone and building materials.



#### TECHNICAL CHARACTERISTICS

<b>Density</b>	: 0,88-0,95 (EΛΟΤ EN ISO 2811 20°C)
<b>Viscosity</b>	: 30 - 100 mPas (ASTM D2196-86 25°C)
<b>Thinning</b>	: 20% with solvent No806
<b>Coverage</b>	: 7 - 8 m <sup>2</sup> /lt depend on the dilution and the surface absorbency
<b>Drying time</b>	: Touch dry after 30 minutes and recoat able after 2 - 3hours
<b>Colors</b>	: Transparent
<b>Packaging</b>	: 2,5lt, 5lt, 20lt
<b>VOC (Volatile Organic Compounds)</b>	: EU limit value for this product Category A: "h", Type:SB, Binding primers: 750g/l (2010). This product contains max 749g/l VOC.
<b>Painting tools</b>	: Brush, roller, pistol Remove as much paint as possible from the equipment in the container and clean it immediately with solvent No803 or No806 and then wash with hot water and soap.
<b>Conditions of application</b>	: Do not apply at temperatures below 10°C and above 35°C.
<b>Storage</b>	: Store at temperatures from 5°C to 40°C. Close the container after every use.

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS & Co E.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, [www.tetralux.gr](http://www.tetralux.gr), e-mail: [contact@tetralux.gr](mailto:contact@tetralux.gr)



## **TECHNICAL DATA SHEET**

**Date of issue: 2021**

---

### **APPLICATION**

#### **Stir well before use**

Surfaces must be clean, dry and free from foreign objects and substances, such as oil, dust, wax, fat or salts.

### **HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION**

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.