



TECHNICAL DATA SHEET

Date of issue: 2020

RELIEF 550

DESCRIPTION

Textured acrylic paint for interior and exterior use. It has protective properties against cold, heat, moisture and sound. It covers excellently any minor surface imperfections.



TECHNICAL CHARACTERISTICS

Density	: 1,50 - 1,62 (ΕΛΟΤ EN ISO 2811 20°C)
Viscosity	: 40.000 - 55.000 mPas (ASTM D2196-86 25°C)
Thinning	: 0 - 5% with water
Coverage	: 0.8 - 2 m ² /lt per layer
Drying time	: Touch dry after 1 - 2 hours
Colors	: A lot of light or medium shades through color system of TETRALUX
Packaging	: 3lt, 9lt
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: "c", Type:WB, Exterior walls of mineral substrate: 40g/l (2010). This product contains max 39g/l VOC.
Painting tools	: Roller Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS & Co E.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, www.tetralux.gr, e-mail: contact@tetralux.gr



TECHNICAL DATA SHEET

Date of issue: 2020

APPLICATION

Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances.

The surfaces painted with hydrochroma are primed with water based primer TETRADUR or solvent based primer TETRADUR. Apply with RELIEF paint roller, dries in 1-2 hours. Dilute with water depending on the desired final form. In the case of very absorbent surfaces, apply a layer of SOVADUR or RELIEF 40% diluted with water. After drying apply the final layer diluted by 0-5%.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.