

TECHNICAL DATA SHEET

Date of issue: 2022

STUCCOFILL GREEN

DESCRIPTION

STUCCOFILL is acrylic finishing putty for large surfaces. It has high resistance to moisture, alkalinity, temperature changes and is used for putting plasterboard, walls (made of plaster or concrete), as well as for decorative applications. It is easily applicable; it has a great filling capability and spreads evenly. It dries quickly without crackling and it is sanded easily, offering a smooth and durable surface without imperfections. Due to its special composition, the joints of plaster board become invisible.



TECHNICAL CHARACTERISTICS

Density	: 1,65 - 1,75 depending on the shade (EAOT EN ISO 2811 20°C)
Thinning	: Without dilution
Coverage	: 1 kg/ m ² per layer thickness 0,5 mm on suitable prepared surfaces
Drying time	: Touch dry after 1 hour and it's rubbed after 2-3hours with sand paper
Packaging	: 800gr , 5 kg, 18 kg
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: "g", Type:WB, Primers: 30g/l (2010). This product contains max 29g/l VOC.
Painting tools	: Spatula Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.



TECHNICAL DATA SHEET

Date of issue: 2022

APPLICATION

Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances.
Processing such as dry sanding will cause powder residue. Use appropriate equipment to protect breathing.

New surfaces	
	It is applied with a spatula without dilution. It is sanded after 2-3hours with sand paper and after it's cleaned it can be painted with emulsion or acrylic water or solvent based paints.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.