



TECHNICAL DATA SHEET

Date of issue: 2020

STUCCOLUX FINE 851

DESCRIPTION

STUCCOLUX fine is a white acrylic putty for interior and exterior use. It has a high resistance to moisture, alkalinity, and temperature changes and is used for putting walls (plaster or concrete), plasterboard, wood as well as for decorative applications. It is easy to work, fills and spreads evenly. It dries quickly without crackling and it is easily sanded, offering a smooth and durable surface without imperfections.



TECHNICAL CHARACTERISTICS

Density	: 1,64 - 1,70 depending on the shade (ΕΛΟΤ EN ISO 2811 20°C)
Thinning	: Without dilution
Coverage	: 2 - 3m ² per kg per layer on suitable prepared surfaces
Drying time	: Touch dry after 1 hour and it's rubbed after 2-3hours with sand paper
Packaging	: 400gr, 800gr, 5kg
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: "g", Type:WB, Primers: 30g/l (2010). This product contains max 29g/l VOC.
Painting tools	: Spatula Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS & Co E.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, www.tetralux.gr, e-mail: contact@tetralux.gr



TECHNICAL DATA SHEET

Date of issue: 2020

APPLICATION

Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances.
Dry sanding will cause powder residue. Use appropriate equipment to protect breathing.

New surfaces	
	It is applied with a spatula without dilution. It is sanded after 2-3 hours with sand paper and after it's cleaned it can be painted with emulsion or acrylic water or solvent based paints.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.