



TECHNICAL DATA SHEET

Date of issue: 2020

TETRALIT 890

DESCRIPTION

Liquid admixture concoction for plasticizing and retarding coagulation of mortars. Replaces lime. It increases the adhesion of the mortar, leaving a smooth surface on plaster without butterflies and tears. It increases the consistency of the mortar, so the plaster does not 'hang'. It increases the strength of masonry, plaster, decorative bricks, paving etc.



TECHNICAL CHARACTERISTICS

Density	: 1,00 - 1,05 (EΛOT EN ISO 2811 20°C)
Viscosity	: 40 mPas (ASTM D2196-86 25°C)
Packaging	: 1lt, 4lt, 20lt
Colors	: Dark brown
Consumption	: 45g per 25kg cement masonry mortar 70g per 25kg cement mortar plaster
Conditions of application	: Do not apply at temperatures below 10oC and above 35oC.
Storage	: Store at temperatures from 5oC to 40oC. Close the container after every use.

APPLICATION

Stir well before use

It must be added to the mixing water, during the preparation of the mortar. Overdose reduces the strength of mortars.



TECHNICAL DATA SHEET

Date of issue: 2020

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION



Warning

Causes serious eye irritation • Keep out of reach of children • If medical advice is needed, have product container or label at hand • Wash thoroughly after handling • Wear protective gloves/protective clothing/eye protection/face protection • IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. • If eye irritation persists: Get medical advice/attention • Dispose of contents/container in accordance with applicable regional, national and local laws and regulations
Tel. POISON CENTER: 210 7793777