



TECHNICAL DATA SHEET

Date of issue: 2020

SOVADUR 908

DESCRIPTION

SOVADUR is an acrylic water based primer containing fine quartz aggregates. Suitable for adhesion improvement of smooth, non absorbent surfaces and absorbent or slightly unsound surfaces.



TECHNICAL CHARACTERISTICS

Density	: 1,42 - 1,45(EΛΟΤΕΝΙΣΟ 2811 20°C)
Viscosity	: 16000 -22000 mPas(ASTMD2196-86 25°C)
Thinning	: 5-10% with water
Coverage	: 10m ² /lt per layer
Drying time	: Touch dry after 1 hour and recoatable after 2-3 hours
Colors	: Unlimited number of shades through tinting system of TETRALUX.
Packaging	: 3lt, 10lt
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: “g”, Type:WB, primers: 30g/l (2010). This product contains max 29g/l VOC
Painting tools	: Brush, roller Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°Cand above 35°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.

MANUFACTURE PAINTS AND VARNISHESTZELOSEV. ANASTASIOS&CoE.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, www.tetralux.gr, e-mail: contact@tetralux.gr



TECHNICAL DATA SHEET

Date of issue: 2020

APPLICATION

Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.