



TECHNICAL DATA SHEET

Date of issue: 2021

MINIO MARINE 912

DESCRIPTION

Powerful alkyd-based anti-corrosive primer for new or painted metallic surfaces. It contains strong anti-corrosive pigments that protect metal from corrosion and rust. It has great flexibility and powerful adhesion. Neutralizes moisture's corrosive effects. It is recommended as a primer on wooden surfaces, especially those exposed outdoors and on wooden boats, in order to protect them against sepsis.



TECHNICAL CHARACTERISTICS

Density	: 1,49 - 1,53 (ΕΛΟΤ EN ISO 2811 20°C)
Viscosity	: 3.500 - 5.000 mPas (ASTM D2196-86 25°C)
Thinning	: 5% with solvent No806
Coverage	: 13 - 14 m ² /lt per layer
Drying time	: Touch dry after 15-30 minutes and recoat able after 12hours
Colors	: Orange
Packaging	: 750ml, 2,5lt, 5lt, 20lt
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: "i", Type:SB, One-pack performance coatings: 500g/l (2010). This product contains max 499g/l VOC.
Painting tools	: Brush, roller, pistol Remove as much paint as possible from the equipment in the container and clean it immediately with solvent No803 or No806 and then wash with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS & Co E.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, www.tetralux.gr, e-mail: contact@tetralux.gr



TECHNICAL DATA SHEET

Date of issue: 2021

APPLICATION

Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances.
It is recommended the application of two layers.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.