



TECHNICAL DATA SHEET

Date of issue: 2020

ACRYLIC FLOOR PAINT

DESCRIPTION

Acrylic floor paint TETRALUX is a special paint of acrylic resins, suitable for concrete floors of industrial areas and sports arenas.



TECHNICAL CHARACTERISTICS

| | |
|---|--|
| Density | : 1,08 – 1,16 (EAOT EN ISO 2811 20°C) |
| Viscosity | : 1.500 – 2.000 mPas (ASTM D2196-86 25°C) |
| Thinning | : 5% with solvent No806 |
| Coverage | : 8 - 11 m ² /l per layer |
| Drying time | : Touch dry after 15 - 30 minutes and recoat able after 6 hours |
| Colors | : RAL shades |
| Packaging | : 5lt, 20lt |
| VOC (Volatile Organic Compounds) | : EU limit value for this product Category A: “i”, Type:SB, One pack performance coatings: 500g/l (2010). This product contains max 499g/l VOC. |
| Painting tools | : Brush, roller, pistol Remove as much paint as possible from the equipment in the container and clean it immediately with solvent No806 and then wash with hot water and soap. |
| Conditions of application | : Do not apply at temperatures below 10°C and above 35°C. |
| Storage | : Store at temperatures from 5°C to 40°C. Close the container after every use. |

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS & Co E.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, www.tetralux.gr, e-mail: contact@tetralux.gr



TECHNICAL DATA SHEET

Date of issue: 2020

APPLICATION

Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.