

TECHNICAL DATA SHEET

Date of issue: 2020

CORROBLOCKER

DESCRIPTION

CORROBLOCKER is a water-based undercoat for rust inactivation. Converts residual rust into a stable organic iron complex and provides long-term corrosion protection. Ensures good penetration of rust and enhances adhesion.



TECHNICAL CHARACTERISTICS

Density	: 1,00 - 1,20 (ΕΛΟΤ EN ISO 2811 20°C)
Viscosity	: ≥ 500 mPas (ASTM D2196-86 25°C)
Thinning	: Without dilution
Coverage	: 7 - 10 m ² /l
Drying time	: The stabilization of rust and change of color to grey-black is completed in 2-3 hours
Packaging	: 375ml, 3l, 10l
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: "i", Type: WB, One-pack performance coatings: 140g/l (2010). This product contains max 139g/l VOC.
Painting tools	: Brush or roller Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 32°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.



TECHNICAL DATA SHEET

Date of issue: 2020

APPLICATION

Stir well before use

Surfaces must be free of oils, grease, loose rust and old paint.

Before application, mix well with wooden stick in the container to be completely homogenized. It is not necessary to apply excess material (consumption 7-10m²/lit) and the stabilization of rust and change of color to grey-black is completed in 2-3 hours. Then the surface can accept any anti-rust primer and final paint.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.