



TECHNICAL DATA SHEET

Date of issue: 2021

HYDROCHROMA COVER FOR MOULD PROTECTION

DESCRIPTION

Hydrochroma COVER for mould protection of TETRALUX is an acrylic based paint for interior use. It prevents the appearance of mould on the dry film. It offers excellent coverage mainly for ceilings, but also for walls of basements, bathrooms, etc., allowing the surface's transpiration and not yellowing, giving a matte, white finish.



TECHNICAL CHARACTERISTICS

Density	: 1,67 - 1,70 (EAOT EN ISO 2811 20°C)
Viscosity	: 9.500 - 11.500 mPas (ASTM D2196-86 25°C)
Thinning	: 15 – 30% with water
Coverage	: 9 – 12m ² /l per layer
Drying time	: Touch dry after 1 hour and it's recoatable after 2-3hours
Colors	: Light shades through tinting system of TETRALUX.
Packaging	: 0.75lt, 3lt, 9lt
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: "a", Type:WB, Interior matt walls and ceilings (Gloss <25@60°): 30g/l (2010). This product contains max 29g/l VOC.
Painting tools	: Brush, roller, pistol Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS & Co E.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, www.tetralux.gr, e-mail: contact@tetralux.gr



TECHNICAL DATA SHEET

Date of issue: 2021

Storage : Store at temperatures from 5°C to 40°C. Close the container after every use.

APPLICATION

Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances.
It is diluted 30% with water for white and 15% for the shades.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.