

TECHNICAL DATA SHEET

Date of issue: 2020

STUCCO VENEZIANO

DESCRIPTION

Decorative stucco based on calcium dihydroxide.



TECHNICAL CHARACTERISTICS

Density	: 1,68-1,71 (EAOT EN ISO 2811 20°C)
Viscosity	: Thixotropic (ASTM D2196-86 25°C)
Thinning	: Without dilution
Coverage	: For 3 layers on smooth surface 0,8 - 0,9 kg/m ²
Packaging	: 1kg, 5kg, 15kg
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: "I", Type:WB, Decorative effect coatings: 200g/l (2010). This product contains max 30g/l.
Painting tools	: Spatula Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.



TECHNICAL DATA SHEET

Date of issue: 2020

APPLICATION

Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances.

The product does not require dilution unless it's necessary.

- a) Apply a layer of PRIMER STUCCO
- b) Tint in your preferred shade. If it is necessary, add while stirring, thickener in order to increase the viscosity to the appropriate workability.
- c) 1st layer: apply one layer of STUCCO VENEZIANO of MONDO BELLO
- d) 2nd layer: after 12 hours stir to soften STUCCO VENEZIANO and apply a second layer
- e) 3rd layer: after 12 hours stir to soften STUCCO VENEZIANO and apply a third layer with irregular moves.

After we have applied on a surface of a square meter and after 30 seconds, we press and polish the surface with a stainless steel spatula. Continue in the same way on the rest of the surface.

Our wall has become glossy with a special effect.

HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.