### **TECHNICAL DATA SHEET** Date of issue: 2021

# **TETRALAC 3 IN 1 METAL MODIFIED** POLYURETHANE DECORATIVE ENAMEL

## **DESCRIPTION**

Anticorrosive and decorative paint of modified alkyd resins with polyurethane. It has sculpted metallic-pearl texture. Applied directly to rusted surfaces. Because of its special composition inactivates rust and protects metal from corrosion and UV radiation.



TECHNICAL CHARACTERISTICS	
Density	: 1,32-1,36 depend on the shade (EAOTENISO 2811 20°C)
Viscosity	: 80-87 KU
Thinning	: 5% with solvent No804 for roller and 10% solvent No806 for pistol
Coverage	: $12 - 13m^2/lt$ per layer
Drying time	: Touch dry after 1 hour and recoat able after 16 hours
Colors	: Base aluminum, shades.
Packaging	: 750ml, 2,5lt, 20lt
VOC (VolatileOrganic Compounds)	: EU limit value for this product Category A: "i", Type:SB, One-pack performance coatings: 500g/l (2010). This product contains max 499g/l VOC.
Painting tools	: Brush, roller, pistol Remove as much paint as possible from the equipment in the container and clean it immediately with solvent No804 or No806 and then washwith hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°Cand above 35°C.
Storage	: Store at temperatures from 5°C to 40°C. Close the container after every use.

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS&CoE.E. 5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI TEL: 2310 796110, FAX: 2310 723096, www.tetralux.gr, e-mail: contact@tetralux.gr



## **APPLICATION**

## Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances.

### HEALTH, SAFETYAND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.