



## TECHNICAL DATA SHEET

Date of issue: 2023

# SOLLIEVO

## DESCRIPTION

Acrylic, decorative coating ready to use. It has excellent adhesion to all masonry types like concrete, plaster, cement, etc. Does not need to be over-coated by paint. Due to its elasticity, it is ideal as topcoat to the constructions for subsequent insulation of buildings.

## TECHNICAL CHARACTERISTICS

<b>Density</b>	: 1,74 - 1,83 (ΕΛΟΤ EN ISO 2811 20°C)
<b>Viscosity</b>	: 40.000 - 55.000 mPas (ASTM D2196-86 25°C)
<b>Thermal conductivity</b>	: $\lambda=0,7$ W(mk)
<b>Thinning</b>	: Without dilution
<b>Coverage</b>	: 2-2.4 m <sup>2</sup> /kg per layer
<b>Drying time</b>	: Touch dry after 1 hour at 25°C
<b>Colors</b>	: Unlimited number of shades through tinting system of TETRALUX. -The raw materials (natural stones and artificial glass beads) in the Sollievo, may produce small differences in the tinting, so it is recommended the tinting of same batches)
<b>Packaging</b>	: 5kg, 18kg, 25kg
<b>VOC (Volatile Organic Compounds)</b>	: EU limit value for this product Category A: "i", Type:WB, One pack performance coatings: 140g/l (2010). This product contains <140g/l VOC.
<b>Painting tools</b>	: Spatula or appropriate machine  Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.
<b>Conditions of application</b>	: Do not apply at temperatures below 8°C and above 38°C.
<b>Storage</b>	: Store at temperatures from 5°C to 40°C. Close the container after every use.

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS & Co E.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, [www.tetralux.gr](http://www.tetralux.gr), e-mail: [contact@tetralux.gr](mailto:contact@tetralux.gr)



## **TECHNICAL DATA SHEET**

**Date of issue: 2023**

---

### **APPLICATION**

#### **Stir well before use**

The substrate must be clean, dry and free of foreign matter and substances. First apply a layer with the special PRIMER SOLLIEVO. After the primer dries, stir the material well and apply using a stainless polished spatula or an appropriate machine. While the SOLLIEVO layer is fresh (about 5-15 minutes later), the surface is 'pressed' or 'scrubbed' using a plastic spatula. Do not apply at temperatures below 8°C and above 38°C and in conditions of relative humidity above 80%.

---

### **HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION**

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.