



## TECHNICAL DATA SHEET

Date of issue: 2020

### PRIMER FOR STUCCO VENEZIANO

#### DESCRIPTION

Primer for STUCCO VENEZIANO applied in one layer. The textured surface it creates offers perfect adhesion and becomes guide for the same film thickness of STUCCO VENEZIANO.



#### TECHNICAL CHARACTERISTICS

<b>Density</b>	: 1,13 - 1,14 (EAOT EN ISO 2811 20°C)
<b>Viscosity</b>	: 7.000 - 8.500 mPas (ASTM D2196-86 25°C)
<b>Thinning</b>	: 10 - 15 %
<b>Coverage</b>	: 8 - 10 m <sup>2</sup> /l per layer
<b>Drying time</b>	: Touch dry after 1 hour
<b>Colors</b>	: Semi transparent
<b>Packaging</b>	: 750ml, 3 lt ,10 lt
<b>VOC (Volatile Organic Compounds)</b>	: EU limit value for this product Category A: "I", Type:WB, Decorative effect coatings: 200g/l (2010). This product contains max 40g/l VOC.
<b>Painting tools</b>	: Roller, brush Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.
<b>Conditions of application</b>	: Do not apply at temperatures below 10°C and above 35°C.
<b>Storage</b>	: Store at temperatures from 5°C to 40°C. Close the container after every use.

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS & Co E.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, [www.tetralux.gr](http://www.tetralux.gr), e-mail: [contact@tetralux.gr](mailto:contact@tetralux.gr)



## **TECHNICAL DATA SHEET**

Date of issue: 2020

---

### **APPLICATION**

#### **Stir well before use**

Surfaces must be clean, dry and free from foreign objects and substances.

Dilute 10-15% with water and apply a layer with roller or brush.

---

### **HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION**

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.