



## TECHNICAL DATA SHEET

Date of issue: 2021

### HYDROCHROMA COVER 860

#### DESCRIPTION

Hydrochroma COVER of TETRALUX is an acrylic based paint for interior use. It offers excellent coverage. Especially suitable for ceilings, but also for walls of basements, bathrooms, etc., allowing the surface's transpiration and non yellowing, giving a matt, white colour.



#### TECHNICAL CHARACTERISTICS

Density	: 1,67 - 1,70 (EAOT EN ISO 2811 20°C)
Viscosity	: 9.500 - 11.500 mPas (ASTM D2196-86 25°C)
Thinning	: 15 - 25% with water
Coverage	: 9 - 12m <sup>2</sup> /l per layer
Drying time	: Touch dry after 1 hour and it's recoatable after 2-3hours
Colors	: Light shades through tinting system of TETRALUX.
Packaging	: 0.75lt, 3lt, 9lt
VOC (Volatile Organic Compounds)	: EU limit value for this product Category A: "a", Type:WB, Interior matt walls and ceilings (Gloss <25@60°): 30g/l (2010). This product contains max 29g/l VOC.
Painting tools	: Brush, roller, pistol Remove as much paint as possible from the equipment in the container and clean it immediately with hot water and soap.
Conditions of application	: Do not apply at temperatures below 10°C and above 35°C.

MANUFACTURE PAINTS AND VARNISHES TZELOS EV. ANASTASIOS & Co E.E.

5A SQUARE 570 22 SINDOS, INDUSTRIAL AREA OF THESSALONIKI

TEL: 2310 796110, FAX: 2310 723096, [www.tetralux.gr](http://www.tetralux.gr), e-mail: [contact@tetralux.gr](mailto:contact@tetralux.gr)



## TECHNICAL DATA SHEET

Date of issue: 2021

**Storage** : Store at temperatures from 5°C to 40°C. Close the container after every use.

## APPLICATION

### Stir well before use

Surfaces must be clean, dry and free from foreign objects and substances.  
It is diluted 25% with water for white and 15% for the shades.

## HEALTH, SAFETY AND ENVIRONMENTAL INFORMATION

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult TETRALUX Safety Data Sheets and follow all local or national safety regulations.